CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

# QC ABSTRACT

**NAME OF WORK:** Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

| SL NO | Item Of Work | Name of Test | Frequency of Test/Quantity | Executed Quantity | Number of Tests Required | Number of Tests Conducted |
|---|---|---|---|---|---|---|
| | | **Materials** | | | | |
| 1 | Cement | Fineness by dry sieving | One Test | | 1 | 1 |
| | | Finess by Air permeablity method | One Test | | 1 | 1 |
| | | Density | One Test | | 1 | 1 |
| | | Standard Consistency | One Test | | 1 | 1 |
| | | Initial Setting time | One Test | | 1 | 1 |
| | | Final Setting time | One Test | | 1 | 1 |
| | | Soundness (Le Chatelier's Method) | One Test | | 1 | 1 |
| | | Compressive Strength | One Test | | 1 | 1 |
| 2 | Coarse aggregate(40 mm down size) | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Flakiness Index | One Test | | 1 | 1 |
| | | Elongation Index | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Bulk Density(Loose) | One Test | | 1 | 1 |
| | | Bulk Density(Compacted) | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| 3 | Coarse aggregate(20 mm down size) | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Flakiness Index | One Test | | 1 | 1 |
| | | Elongation Index | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Bulk Density(Loose) | One Test | | 1 | 1 |
| | | Bulk Density(Compacted) | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| | | Aggregate crushing Value | One Test | | 1 | 1 |
| | | Aggregate Impact Value | One Test | | 1 | 1 |
| 4 | Fine aggregate | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Material finer than 75 micron | One Test | | 1 | 1 |
| 5 | Steel | Bend test | One Test | | 1 | 1 |
| | | Tensile Test | One Test | | 1 | 1 |
| | | Yield Test | One Test | | 1 | 1 |
| | | ReBend test | One Test | | 1 | 1 |
| 6 | Precast (100mm) | Core Compressive Strength | One Test | | 1 | 1 |
| | | Corrected Cylinder Compressive Strength | One Test | | 1 | 1 |
| | | Equivalent Cube Compressive Strength | One Test | | 1 | 1 |
| 7 | RCC(M20) | Compressive Strength(7days and 28days) | 6 sets /100-150 cum | 113.4 | 12 | 12 |

AB-14

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ವಿದ್ಯಾರಣ್ಯಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ, ಬೆಂಗಳೂರು-97

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO

AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017

# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2023-12-08-03** **Date: 03-10-23** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura) |
| **Agency** | : | Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032 |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/170/2022-23 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 29-09-23 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 269:2015 Ordinary Portland cement Specification ,<br>IS 4031 (Part 4,5):1988<br>IS 4031 Part 1 (RA 2021) DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4<br>IS 4031 Part 2, (RA 2018) Determination of Fineness by Blaine Air Permeability Method, Clause 5<br>IS 4031 Part 3, (RA 2019) Determination of Soundness, Clause 5, Clause 6<br>IS 4031 Part 4, (RA 2019) Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 5, (RA 2019) Determination of Initial & Final Setting Time, Clause 5<br>IS 4031 Part 11, (RA 2019)DETERMINATION OF DENSITY , Clause 6 |
| **Date of test** | : | 30-09-23 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

| Sl.No. | Physical properties | Results | Requirement as per IS 269:2015 |
|---|---|---|---|
| 1 | Fineness by dry sieving (%) | 1.75 | – |
| 2 | Finess by Air permeablity method ($m^2$/kg,Min) | 281.4 | 225$m^2$/kg, Min |
| 3 | Density (gm/cc) | 3.14 | – |
| 4 | Standard Consistency (%) | 29.5% | Not specified |
| 5 | Initial Setting time | 155 minutes | Not less than 30 minutes |
| 6 | Final Setting time | 285 minutes | Not more than 600 minutes |
| 7 | Soundness (Le Chatelier's Method) | 2mm | Not more than 10 mm |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.

All information furnished by Agency/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**

Authorized Signatory

**Quality Manager**

Page 1/1

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2023-12-08-03** **Date: 28-10-23** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura) |
| **Agency** | : | Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032 |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/170/2022-23 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 29-09-23 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 269:2015 Ordinary Portland cement Specification , IS 4031 (Part 4,5):1988<br>IS 4031 Part 4, (RA 2019) Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 6, (RA 2019) Determination of Compressive Strength, Clause 6 |
| **Date of test** | : | 30-09-23 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

**Compressive Strength**

| Sl.No. | Physical properties | Results | Requirement as per IS 269:2015 |
|---|---|---|---|
| 1 | 3 Days | 28.5N/mm$^2$ | Not less than 27 N/mm$^2$ |
| 2 | 7 Days | 39.0N/mm$^2$ | Not less than 37 N/mm$^2$ |
| 3 | 28 Days | 58.5N/mm$^2$ | Not less than 53 N/mm$^2$ |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2023-12-08-03** **Date: 03-10-23** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura) |
| **Agency** | : | Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032 |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/170/2022-23 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample condition** | : | Satisfactory |
| **Date of Receipt** | : | 29-09-23 |
| **Sample Type** | : | 40mm down size coarse aggregate |
| **Reference to BIS codes** | : | IS: 383:2016 (Specification for Coarse and fine Aggregates )<br>IS: 2386 :1963(Part - 1,3,4) RA2021<br>IS 2386 Part 1: Particle Size and Shape<br>IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption<br>IS 2386 Part 4: Mechanical Properties |
| **Date of test** | : | 29-09-23 |

**SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:**

**Total weight taken : 15000 grams**

| Sample No. | Sieve No. | Weight Retained in gms | Cumulative Weight Retained in gms | % Cumulative Weight Retained | % Passing | Required as per IS 383:2016 |
|---|---|---|---|---|---|---|
| 1 | 80 mm | 0 | 0 | 0.0 | 100 | 100 |
| 2 | 40 mm | 218 | 218 | 1.5 | 98.5 | 90-100 |
| 3 | 20 mm | 7289 | 7507 | 50.0 | 50.0 | 30-70 |
| 4 | 10 mm | 5102 | 12609 | 84.1 | 15.9 | 10-35 |
| 5 | 4.75 mm | 2185 | 14794 | 98.6 | 1.4 | 0-5 |
| 6 | Pan | 206 | 15000 | 100.0 | 0 | --- |



CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

**Lab ID** : **CP-2023-12-08-03** **Date: 03-10-23**

**PHYSICAL PROPERTIES**

| Sl.no | Tests | Result | Requirements as per IS:383-2016 |
|---|---|---|---|
| 1 | Flakiness Index(%) | 11.8 | Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate |
| 2 | Elongation Index(%) | 12.5 | |
| 3 | Specific Gravity | 2.62 | _ |
| 4 | Bulk Density(Loose) (Kg/l) | 1.48 | _ |
| 5 | Bulk Density(Compacted) (Kg/l) | 1.51 | _ |
| 6 | Water Absorption(%) | 0.18 | _ |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**


****End of Report****

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2023-12-08-03** **Date: 03-10-23** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura) |
| **Agency** | : | Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032 |
| **Customer Reference** | : | BBMP/EE/BTP/WO/170/2022-23 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 29-09-23 |
| **Sample Type/ Size** | : | 20mm down size coarse aggregate |
| **Reference to BIS codes** | : | IS: 383:2016 (Specification for Coarse and fine Aggregates )<br>IS: 2386 :1963(Part - 1,3,4) RA2021<br>IS 2386 Part 1: Particle Size and Shape<br>IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption<br>IS 2386 Part 4: Mechanical Properties |
| **Date of test** | : | 29-09-23 |

**SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:**

**Total weight taken : 5000 grams**

| Sample No. | Sieve No. | Weight Retained in gms | Cumulative Weight Retained in gms | % Cumulative Weight Retained | % Passing | Required as per IS 383:2016 |
|---|---|---|---|---|---|---|
| 1 | 40 mm | 0 | 0 | 0 | 100 | 100 |
| 2 | 20 mm | 240 | 240 | 4.8 | 95.2 | 90-100 |
| 3 | 10 mm | 2567 | 2807 | 56.1 | 43.9 | 25-55 |
| 4 | 4.75 mm | 2030 | 4837 | 96.7 | 3.3 | 0-10 |
| 5 | Pan | 163 | 5000 | 100 | 0 | – |



CIVIL Pro Sig Date BANGALORE

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

**Lab ID** : **CP-2023-12-08-03** **Date: 03-10-23**

### PHYSICAL PROPERTIES

| Sl.no | Tests | Result | Requirements as per IS:383-2016 |
|---|---|---|---|
| 1 | Flakiness Index(%) | 9.8 | Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate |
| 2 | Elongation Index(%) | 10.3 | |
| 3 | Specific Gravity | 2.65 | _ |
| 4 | Bulk Density(Loose) (Kg/l) | 1.5 | _ |
| 5 | Bulk Density(Compacted) (Kg/l) | 1.52 | _ |
| 6 | Water Absorption(%) | 0.23 | _ |
| 7 | Aggregate crushing Value(%) | 22.7 | Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface. |
| 8 | Aggregate Impact Value(%) | 24.6 | 30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface. |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signature
**Quality Manager**


*End of Report*

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF FINE AGGREGATE

**Lab ID** : **CP-2023-12-08-03** **Date: 03-10-23**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 29-09-23

**Sample Type** : Fine Aggregate

**Reference to BIS codes** : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2021
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

**Date of test** : 29-09-23

**Total weight taken** : 1000 grams

| Sl.no | Sieve Size | Weight Retained (gms) | Cumulative Weight Retained (gms) | % Cumulative Weight Retained | % Passing | Requirement as per IS 383:2016 | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | | | | | Grading Zone I | Grading Zone II | Grading Zone III | Grading Zone IV |
| 1 | 10 mm | 0 | 0 | 0.0 | 100.0 | 100 | 100 | 100 | 100 |
| 2 | 4.75 mm | 78 | 78 | 7.8 | 92.2 | 90-100 | 90-100 | 90-100 | 95-100 |
| 3 | 2.36 mm | 65 | 143 | 14.3 | 85.7 | 60-95 | 75-100 | 85-100 | 95-100 |
| 4 | 1.18 mm | 244 | 387 | 38.7 | 61.3 | 30-70 | 55-90 | 75-100 | 90-100 |
| 5 | 600 micron | 215 | 602 | 60.2 | 39.8 | 15-34 | 35-59 | 60-79 | 80-100 |
| 6 | 300 micron | 178 | 780 | 78.0 | 22.0 | 5-20 | 8-30 | 12-40 | 15-50 |
| 7 | 150 micron | 141 | 921 | 92.1 | 7.9 | 0-10 | 0-10 | 0-10 | 0-15 |
| 8 | Pan | 79 | 1000 | 100.0 | 0.0 | --- | --- | --- | --- |

**Result :The tested Sample Conforms to Grading Zone II**



CIVIL Pro Sig. Date. BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

# TEST REPORT OF FINE AGGREGATE

**Lab ID** : **CP-2023-12-08-03** **Date: 03-10-23**

## PHYSICAL PROPERTIES

| Sl.no | Tests | Result | Requirements as per IS 383:2016 |
|---|---|---|---|
| 1 | Water Absorption(%) | 1.5 | – |
| 2 | Specific Gravity | 2.59 | – |
| 3 | Material finer than 75 micron(%) | 7.9 | Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10% |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**

83
DR-14


****End of Report****

ಸಹಾಯಕ ಆಯುಕ್ತರು ಆಧಿಪತ್ಯದಲ್ಲಿ
ಮಲ್ಲೇಶ್ವರಂ ಉಪ ವಿಭಾಗ
ಬೆಂಗಳೂರು-97

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST RESULTS OF STEEL

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2023-12-08-03** **Date: 30-09-23** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura) |
| **Agency** | : | Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032 |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/170/2022-23 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 29-09-23 |
| **Sample Type** | : | Sunvik |
| **Reference to BIS codes** | : | IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2019. |
| **Date of test** | : | 29-09-23 |

| Sl.No | Identification of sample | Grade of the sample | Diameter of the steel bar | Weight of the sample | Yield stress | Tensile strength | Elongation | Bend test | Rebend test |
|---|---|---|---|---|---|---|---|---|---|
| | | | (mm) | (kg/m) | (N/mm2) | (N/mm2) | (%) | | |
| 1 | Sunvik | Fe500 | 8 | 0.391 | 512 | 652 | 20.0% | Satisfactory | Satisfactory |
| 2 | Sunvik | Fe500 | 10 | 0.616 | 528 | 672 | 20.0% | Satisfactory | Satisfactory |
| 3 | Sunvik | Fe500 | 12 | 0.888 | 544 | 668 | 20.0% | Satisfactory | Satisfactory |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

**R KARTHIK RECHAN**
**Authorized Signatory**
**Quality Manager**


*End of Report*

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF PRECAST COVER SLAB

**Lab ID** : **CP-2023-12-08-03** **Date: 16-10-23**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Sample Type /Size** : Precast Cover Slab - 100mm thickness

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete

**Date of test** : 12/10/2023

**Grade of Slab** : M15

| Sl. No. | Identification Mark | Diameter of the core | Height of the core | Weight of the core | Area | Failure Load | Core Compressive strength | Corrected Cylinder Compressive strength | Equivalent Cube Compressive strength |
|---|---|---|---|---|---|---|---|---|---|
| | | (mm) | (mm) | (kg) | (Sq.mm) | (KN) | ($N/mm^2$) | ($N/mm^2$) | ($N/mm^2$) |
| 1 | Cover Slab-1 | 77.52 | 100.48 | 1.116 | 4719 | 80.9 | 17.1 | 15.9 | 19.9 |
| 2 | Cover Slab-2 | 77.49 | 100.52 | 1.122 | 4715 | 82.3 | 17.5 | 16.2 | 20.3 |
| 3 | Cover Slab-3 | 77.51 | 100.51 | 1.118 | 4718 | 81.5 | 17.3 | 16.1 | 20.1 |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager



****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 17/10/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Customer ID** : Drain Bottom Raft Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 17/10/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.87 X 150.70 X 150.21 | 22736 | 8.773 | 339.7 | 14.9 | 14.7 |
| 2 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.25 X 150.13 X 150.29 | 22557 | 8.851 | 323.1 | 14.3 | |
| 3 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.87 X 150.48 X 150.61 | 22703 | 8.210 | 334.4 | 14.7 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**

Page 1/1
****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 07/11/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Customer ID** : Drain Bottom Raft Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 07/11/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.66 X 150.22 X 150.49 | 22631 | 8.541 | 532.5 | 23.5 | 23.3 |
| 2 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.56 X 150.27 X 150.39 | 22626 | 8.872 | 521.7 | 23.1 | |
| 3 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.98 X 150.10 X 150.36 | 22663 | 8.881 | 530.0 | 23.4 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 17/10/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Customer ID** : Drain Bottom Raft Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 17/10/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.75 X 150.52 X 150.33 | 22691 | 8.458 | 323.0 | 14.2 | 14.6 |
| 2 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.43 X 150.08 X 150.58 | 22576 | 8.287 | 332.7 | 14.7 | |
| 3 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.97 X 150.99 X 150.59 | 22795 | 8.450 | 336.7 | 14.8 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 07/11/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Customer ID** : Drain Bottom Raft Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 07/11/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.94 X 150.89 X 150.18 | 22775 | 8.248 | 527.7 | 23.2 | 23.4 |
| 2 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.87 X 150.94 X 150.96 | 22772 | 8.192 | 536.4 | 23.6 | |
| 3 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.87 X 151.00 X 150.42 | 22781 | 8.146 | 531.8 | 23.3 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**



****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 17/10/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Customer ID** : Drain Bottom Raft Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 17/10/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.84 X 150.87 X 150.56 | 22757 | 8.537 | 322.3 | 14.2 | 14.5 |
| 2 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.36 X 150.93 X 150.04 | 22695 | 8.775 | 328.0 | 14.5 | |
| 3 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 17/10/2023 | 150.26 X 150.05 X 150.98 | 22546 | 8.170 | 336.0 | 14.9 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 07/11/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 12-10-23

**Customer ID** : Drain Bottom Raft Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 07/11/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.24 X 150.79 X 150.31 | 22655 | 8.655 | 536.5 | 23.7 | 23.4 |
| 2 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.07 X 150.11 X 150.24 | 22526 | 8.509 | 527.2 | 23.4 | |
| 3 | Drain Bottom Raft Concrete | M20 | 10/10/2023 | 07/11/2023 | 150.77 X 150.83 X 150.79 | 22740 | 8.422 | 526.9 | 23.2 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 20/10/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 16-10-23

**Customer ID** : Drain Side Wall Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 20/10/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.88 X 150.60 X 150.31 | 22722 | 8.655 | 320.2 | 14.1 | 14.4 |
| 2 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.78 X 150.24 X 150.70 | 22653 | 8.670 | 335.3 | 14.8 | |
| 3 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.52 X 150.90 X 150.63 | 22714 | 8.495 | 326.9 | 14.4 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 10/11/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 16-10-23

**Customer ID** : Drain Side Wall Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 10/11/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.43 X 150.25 X 150.92 | 22601 | 8.249 | 536.9 | 23.8 | 23.6 |
| 2 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.39 X 150.69 X 150.76 | 22662 | 8.274 | 531.0 | 23.4 | |
| 3 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.79 X 150.98 X 150.87 | 22766 | 8.969 | 534.5 | 23.5 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

183
-12-14

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ವಿದ್ಯಾರಣ್ಯಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-97


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 20/10/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 16-10-23

**Customer ID** : Drain Side Wall Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 20/10/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.42 X 150.43 X 150.33 | 22628 | 8.634 | 323.1 | 14.3 | 14.4 |
| 2 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.64 X 150.48 X 150.37 | 22668 | 8.818 | 334.8 | 14.8 | |
| 3 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.39 X 150.71 X 150.21 | 22665 | 8.964 | 323.9 | 14.3 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 10/11/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 16-10-23

**Customer ID** : Drain Side Wall Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 10/11/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.05 X 150.25 X 150.22 | 22545 | 8.698 | 540.2 | 24.0 | 23.7 |
| 2 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.64 X 150.77 X 150.26 | 22712 | 8.754 | 524.8 | 23.1 | |
| 3 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.70 X 150.03 X 150.61 | 22609 | 8.509 | 542.0 | 24.0 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**

Page 1/1
****End of Report****

ನಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ವಿದ್ಯಾರಣ್ಯಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-97

CIVIL PRO

AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017

# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 20/10/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 16-10-23

**Customer ID** : Drain Side Wall Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 20/10/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.79 X 150.49 X 150.46 | 22692 | 8.605 | 325.0 | 14.3 | 14.6 |
| 2 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.91 X 150.25 X 150.90 | 22675 | 8.962 | 337.5 | 14.9 | |
| 3 | Drain Side Wall Concrete | M20 | 13/10/2023 | 20/10/2023 | 150.08 X 150.85 X 150.85 | 22639 | 8.140 | 328.2 | 14.5 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**



****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2023-12-08-03** **Date: 10/11/2023**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : Improvements to Roads and Drains at Annapurneshwari Layout, Sapthagiri Layout and Surrounding area in Ward No 14 (Vidyaranyapura)

**Agency** : Sri. B P Shanmugam, #28/2, 2nd Cross, Giddappa Block, Ganganagar, Bengaluru-560032

**Customer's Reference** : BBMP/EE/BTP/WO/170/2022-23

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 16-10-23

**Customer ID** : Drain Side Wall Concrete

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M20 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 10/11/2023

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.04 X 150.51 X 150.17 | 22582 | 8.211 | 530.8 | 23.5 | 23.6 |
| 2 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.96 X 150.94 X 150.27 | 22786 | 8.553 | 533.6 | 23.4 | |
| 3 | Drain Side Wall Concrete | M20 | 13/10/2023 | 10/11/2023 | 150.15 X 150.62 X 150.83 | 22614 | 8.735 | 542.0 | 24.0 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com